

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 883 171

Internet: www.awqc.com.au

Email: producttesting@awqc.com.au



LiquiMix Pty Ltd
Attn: Bryant Wells
PO Box 108
Brisbane Market
QLD 4106
AUSTRALIA

20/04/2021

Dear Bryant,

Please find the attached report to AS/NZS 4020:2018 for Civiox LV100 Three Coat System submitted for testing.

Should you have any enquiries about the report or any other matters pertaining to the Standard please contact the laboratory on 61 8 7424 1512

Yours sincerely,

Michael Glasson
Supervisor Product Testing



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

Report Information

Submitting Organisation : 00120664 : LiquiMix Pty Ltd
Account : 141294 : LiquiMix Pty Ltd
AWQC Reference : 141294-2020-CSR-1 : Prod Test: Civilox LV100 System
Project Reference : PT-4420
Product Designation : Civilox LV100 Three Coat System
Composition of Product : 1st Coat - Civilox LV100, 1st & 2nd Coat - Civilox LV100, Civilox HB200 and 1st, 2nd & 3rd Coat - Civilox LV100, Civilox HB200 and Elaston W80.
Product Manufacturer : Liquimix Pty Ltd., Rosa Place, Richlands, QLD, AUSTRALIA.
Use of Product : In-Use/Coating System (Three Coat).
Sample Selection: As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2018

Extracts : Extracts were prepared as described in Appendix/Clause C, D, E, F, H, 6.8.
Project Completion Date : 19-Apr-2021
Project Comment : The results presented herein demonstrate compliance to AS/NZS 4020:2018 for Civilox LV 100 Three Coat System exposed at an area to volume ratio of 1000 mm²/L respectively at 20°C ± 2°C.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson
APPROVED SIGNATORY

FINAL REPORT

Report ID : 307585

Summary of Results

APPENDIX/CLAUSE	RESULTS
C – Taste	Passed at an exposure of 1000 mm ² per Litre respectively for each coating.
D – Appearance	Passed at an exposure of 15000 mm ² per Litre respectively.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 7950 mm ² per Litre respectively with a 0.53 scaling factor applied.
F – Cytotoxic Activity	Passed at an exposure of 15000 mm ² per Litre respectively.
H – Metals	Passed at an exposure of 15000 mm ² per Litre respectively.
6.8 – Organic Compounds	Passed at an exposure of 15000 mm ² per Litre respectively.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2018
D	TO029-01 & TO018-01	APHA 2120c & APHA 2130b
E	TO014-03	APHA 4500 O G
F	TM-001	AS/NZS 4020:2018
H	TIC-006	EPA 200.8

Organic Test Methods

Test(s) in Clause	Test Method	Reference Method
Clause 6.8	TMZ-M36	USEPA524.2
	EP239	USEPA521
	EP132-LL	USEPA_SW846-8270D
	EP075C	USEPA_SW846-8270D
	EP075ASIM	USEPA_SW846-8270D

Summary Comment : Coating systems applied and cured by the submitting organisation prior to submission to AWQC.



Internet: www.awqc.com.au

Email: producttesting@awqc.com.au

FINAL REPORT

Report ID : 307585

CLAUSE 6.2

Taste

Sample Description

The sample consisted of a three coat system providing a surface area of approximately 1000 mm² per Litre respectively. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Taste (Appendix C)

Test Information

Scaling Factor

Not applied.

Results

Not detected (sample and controls).

Evaluation

The product passed the requirements of clause 6.2 when tested at an exposure of 1000 mm² per Litre respectively.

Number of Samples

4.

Test Comment

Panellists detected chemical, iodine, plastic and rubber tastes in the final (7th) extracts when tested at an exposure of 7950mm²/L respectively at 20°C. Test repeated with each coating at 1000mm²/L where no tastes were detected in final (7th) extracts.

Michael Glasson

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

CLAUSE 6.3 Appearance

Sample Description The sample consisted of a three coat system providing a surface area of approximately 15000mm²/L, 5000mm²/L and 2500mm²/L respectively. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Appearance (Appendix D)

Scaling Factor Not applied.

Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 15000 mm² per Litre respectively.

Number of Samples 1.

Test Comment Not applicable.



Andrew Ford

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample consisted of a three coat system providing a surface area of approximately 15000mm²/L, 5000mm²/L and 2500mm²/L respectively. Extracts were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor A scaling factor of 0.53 was applied.

Results

Mean Dissolved Oxygen	Control	7.3 mg/L
Mean Dissolved Oxygen Difference	Positive Reference	5.2 mg/L
	Negative Reference	<0.1 mg/L
	Test	2.40 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 7950 mm² per Litre respectively with a 0.53 scaling factor applied.

Number of Samples 1.

Test Comment The arithmetic mean of nine dissolved oxygen values exceeded the maximum allowable concentration for MDOD. A scaling factor of 0.53 was applied to meet the requirements of Clause 6.4.



Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

CLAUSE 6.5 Cytotoxic Activity

Sample Description	The sample consisted of a three coat system providing a surface area of approximately 15000mm ² /L, 5000mm ² /L and 2500mm ² /L respectively. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
Extraction Temperature	20°C ± 2°C.
Test Method	Cytotoxic Activity (Appendix F)
Scaling Factor	Not applied.
Results	Non-cytotoxic (sample and controls).
Evaluation	The product passed the requirements of clause 6.5 when tested at an exposure of 15000 mm ² per Litre respectively.
Number of Samples	1.
Test Comment	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Mira Maric

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

CLAUSE 6.7

Metals

Sample Description

The sample consisted of a three coat system providing a surface area of approximately 15000mm²/L, 5000mm²/L and 2500mm²/L respectively. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature

20°C ± 2°C.

Test Method

Metals (Appendix H)

Scaling Factor

Not applied.

Method of Analysis

All methods used to determine concentrations of metals are based on those described in the US EPA method 200.8 Determination of Trace elements in Waters and Wastes by Inductively Coupled Plasma - Mass Spectrometry. The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre.

Concentration of the metals described in Table 2 of the AS/NZS 4020:2018 are determined as follows:

Aluminium, Antimony, Arsenic, Barium, Boron, Cadmium, Chromium, Copper, Iron, Lead, Manganese, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass Spectrometry.

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Aluminium	0.001	0.004	0.005	0.005	0.2
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.01
Barium	0.0005	<0.0005	0.0114	0.0111	0.7
Boron	0.020	<0.020	<0.020	<0.020	1.4
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	0.0001	<0.0001	<0.0001	2.0
Iron	0.0005	<0.0005	<0.0005	<0.0005	0.3
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Manganese	0.0001	<0.0001	<0.0001	<0.0001	0.1
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation

The product passed the requirements of clause 6.7 when tested at an exposure of 15000 mm² per Litre respectively.

Number of Samples

1.

Test Comment

Not applicable.



Dzung Bui

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025



FINAL REPORT

Report ID : 307585

CLAUSE 6.8 Organic Compounds

Sample Description The sample consisted of a three coat system providing a surface area of approximately 15000m²/L, 5000mm²/L and 2500mm²/L respectively. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Organic Compounds (Clause 6.8). Max Allowed values are taken from the Australian Drinking Water Guidelines and Drinking-water Standards for New Zealand. Please note, some reported compounds have no guideline value.

Scaling Factor Not applied.

Results

Organic Compound

Nitrosamines	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2039217	ES2039217	
1-Nitrosopiperidine (NPip)	<0.003	<0.003	
1-Nitrosopyrrolidine (NPyr)	<0.01	<0.01	
Nitrosomorpholine (NMor)	<0.003	<0.003	
N-Nitrosodiethylamine (NDEA)	<0.01	<0.01	
N-Nitrosodimethylamine (NDMA)	<0.003	<0.003	0.1 µg/L
N-Nitrosodi-n-propylamine (NDPA)	<0.003	<0.003	
N-Nitrosomethylethylamine (NMEA)	<0.003	<0.003	

Organic Compound

Phenols	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2039217	ES2039217	
2 4 5-trichlorophenol	<1.0	<1.0	
2 4 6-trichlorophenol	<1.0	<1.0	20 µg/L
2 4-dichlorophenol	<1.0	<1.0	200 µg/L
2 4-dimethylphenol	<1.0	<1.0	
2 6-dichlorophenol	<1.0	<1.0	
2-chlorophenol	<1.0	<1.0	300 µg/L
2-nitrophenol	<1.0	<1.0	
4-chloro-3-methylphenol	<1.0	<1.0	
m+p cresol	<2.0	<2.0	
o-cresol	<1.0	<1.0	
pentachlorophenol	<2.0	<2.0	9 µg/L
phenol	<1.0	2.6	

FINAL REPORT

Report ID : 307585

Organic Compound

Phthalate Esters

	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2039217	ES2039217	
Bis(2-ethylhexyl) phthalate	<10	<10	10 µg/L
Butyl benzyl phthalate	<2	<2	
Di(2-ethylhexyl) adipate	<2	<2	
Diethyl phthalate	<2	<2	
Dimethyl phthalate	<2	<2	
Di-n-butyl phthalate	<2	<2	
Di-n-octyl phthalate	<2	<2	

Organic Compound

Polycyclic Aromatic Hydrocarbons

	Blank µg/L	Test µg/L	Max Allowed
!External Lab Report No.	ES2039217	ES2039217	
Acenaphthene	<0.02	<0.02	
Acenaphthylene	<0.02	<0.02	
Anthracene	<0.02	<0.02	
Benzo(a)anthracene	<0.02	<0.02	
Benzo(a)pyrene	<0.005	<0.005	0.01 µg/L
Benzo(a)pyrene TEQ	<0.005	<0.005	
Benzo(b+j)fluoranthene	<0.02	<0.02	
Benzo(ghi)perylene	<0.02	<0.02	
Benzo(k)fluoranthene	<0.02	<0.02	
Chrysene	<0.02	<0.02	
Dibenzo(a-h)anthracene	<0.02	<0.02	
Fluoranthene	<0.02	<0.02	
Fluorene	<0.02	<0.02	
Indeno(123-cd)pyrene	<0.02	<0.02	
Naphthalene	<0.02	<0.02	
PAH - Total	<0.005	<0.005	
Phenanthrene	<0.02	<0.02	
Pyrene	<0.02	<0.02	

FINAL REPORT

Report ID : 307585

Organic Compound

Volatile Organic Compounds GCMS

	Blank µg/L	Test µg/L	Max Allowed
1 1 1 2-Tetrachloroethane	<1	<1	
1 1 1-Trichloroethane	<1	<1	
1 1 2 2-Tetrachloroethane	<1	<1	
1 1 2-Trichloroethane	<1	<1	
1 1-Dichloropropene	<1	<1	
1 2 3-Trichlorobenzene	<1	<1	
1 2 3-Trichloropropane	<1	<1	
1 2 4-Trichlorobenzene	<1	<1	
1 2 4-Trimethylbenzene	<1	<1	
1 2-Dibromo-3-chloropropane	<1	<1	1 µg/L
1 2-Dibromoethane	<1	<1	1 µg/L
1 2-Dichlorobenzene	<1	<1	1500 µg/L
1 2-Dichloroethane	<1	<1	3 µg/L
1 2-Dichloropropane	<1	<1	
1 3 5-Trimethylbenzene	<1	<1	
1 3-Dichlorobenzene	<1	<1	
1 3-Dichloropropane	<1	<1	
1 4-Dichlorobenzene	<1	<1	40 µg/L
1,1-Dichloroethane	<1	<1	
1,1-Dichloroethene	<1	<1	30 µg/L
2,2-Dichloropropane	<1	<1	
2-Chlorotoluene	<1	<1	
4-Chlorotoluene	<1	<1	
4-Isopropyltoluene	<1	<1	
Benzene	<1	<1	1 µg/L
Bromobenzene	<1	<1	
Bromochloromethane	<1	<1	
Bromodichloromethane	<1	<1	60 µg/L
Bromoform	<1	<1	100 µg/L
Bromomethane	<4	<4	
Carbon tetrachloride	<1	<1	3 µg/L
Chlorobenzene	<1	<1	300 µg/L
Chloroethane	<4	<4	
Chloroform	<1	<1	400 µg/L
Chloromethane	<4	<4	
cis-1 3-Dichloropropene	<1	<1	
cis-1,2-Dichloroethene	<1	<1	
Dibromochloromethane	<1	<1	150 µg/L
Dibromomethane	<1	<1	
Dichlorodifluoromethane	<1	<1	
Dichloromethane	<4	<4	4 µg/L
Ethylbenzene	<1	16	300 µg/L
Hexachlorobutadiene	<0.7	<0.7	0.7 µg/L
Isopropylbenzene	<1	<1	
m+p-Xylenes - Total	<2	62	

FINAL REPORT

Report ID : 307585

Organic Compound

Organic Compound	Blank	Test	Max Allowed
Volatile Organic Compounds GCMS	µg/L	µg/L	
Naphthalene	<1	<1	
n-Butylbenzene	<1	<1	
n-Propylbenzene	<1	<1	
o-Xylene	<1	23	
sec-Butylbenzene	<1	<1	
Styrene	<1	<1	30 µg/L
tert-Butylbenzene	<1	<1	
Tetrachloroethene	<1	<1	50 µg/L
Toluene	<1	1	800 µg/L
Total 1,2-dichloroethene	<2	<2	60 µg/L
Total 1,3-dichloropropene	<2	<2	20 µg/L
Total Trichlorobenzene	<2	<2	30 µg/L
Total Xylene	<3	85	600 µg/L
trans-1,3-Dichloropropene	<1	<1	
trans-1,2-Dichloroethene	<1	<1	
Trichloroethene	<1	<1	
Trichlorofluoromethane	<1	<1	
Trihalomethanes - Total	<4	<4	250 µg/L
Vinyl chloride	<0.3	<0.3	0.3 µg/L

Evaluation The product passed the requirements of clause 6.8 when tested at an exposure of 15000 mm² per Litre respectively.

Number of Samples 1.

Test Comment Not applicable.



Qiong Huang

APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

