

Renderfill®-F300

Sand Render Blend

PRODUCT

DESCRIPTION Renderfill-F300 is a unique blend of triple washed fine sand and specialised powder additives

INTENDED

USES

Rendering of concrete when mixed with Civilox-LV100, Civilox-LV110 or Civilox-HB200.
Also the sand seeding of Civilox-LV100 or Civilox-LV110

FEATURES

- Triple washed
- Dry
- Fine White Sand mixture

PRODUCT DATA

Quartz Content	99%
Density	2.63

RENDERING

Civilox (L)	Renderfill-F300 (L)	Mixed Volume (L)	Mixed Consistency
1	1 - 1.5	2 - 2.5	Wet Screed
1	1.5 - 2	2.5 - 3	Pourable (Cake Batter)
1	2 - 2.5	2 - 3.5	Dry Screed

Tested at 25°C, 50% Humidity

Render needs to determine the mix that best suits the substrate condition, temperature, humidity and preference of the render. The substrate must be prepared and sealed with Civilox-LV100 prior to rendering.

SURFACE PREP

& APPLICATION

- Vapour Blast the concrete substrate and remove all unsound concrete
- Remove all dust and loose material
- Check the atmospheric conditions to ensure the temperature of the surface to which the product is to be applied is a minimum of 3°C above the Dew point at the time of application
- Make sure the moisture content of the concrete is below 7%
- Seal the prepared concrete with Civilox-LV100 or Civilox-LV110
- Mix Civilox at 1:1 for 2 minutes then add Renderfill-F300 to the required consistency. Use the above rendering table as a guideline to mixing a usable render.

LIMITATIONS

- The substrate must be sealed prior to trowelling of render
- Tools require cleaning with Reactor Flush

Renderfill®-F300

STORAGE

Store in a dry location. Protect contents from moisture.

PACK SIZE

20Kg Bag

HEALTH & SAFETY

Please refer to and thoroughly read the SDS as published on the Liquimix website, prior to using Liquimix products.

DISCLAIMER

The information contained herein is offered without charge and is for use by technically qualified personnel at their own risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and no warranty of any kind is made with respect thereto.

LiquiMix Pty Ltd - ABN 32 062 887 585
24 Rosa Place, Richlands QLD 4077
Phone: 1300 123 085

Web: - www.liquimix.com
Sales Enquiries: - sales@liquimix.com
Account Enquiries: - accounts@liquimix.com