

STEP 01

Aralox FL - 150 (Sealer / Primer)

DFT : 200 μ m

Comment : Rolled on to prevent topcoat binder absorption and air bubbles

STEP 02

Aralox FL - 170 (Top Coat)

DFT : 250 - 500 μ m

Comment : Squeegee or roller applied in a single coat

STEP 02

Aralox FL - 170

STEP 01

Aralox FL - 150